CIVIL QUALITY CONSULTANTS & ENGINEERS

(Buildings Geo-Tech & Highway Materials Testing Laboratory)
An ISO 9001: 2008 Certified Company

JAS-ANZ
ISO 9001:2000 CERTIFIED

Job No.: CQCE/BBMP/SLE/W.No.14/2017-18 29.12.2017

TEST REPORT ON COMPRESSIVE STRENGTH OF CONCRETE CUBES

Client : **Executive Engineer,** Dasarahalli Division, BBMP, Bangalore.

Agency : **M/s. Shri Lakshmi Enterprises,** Bangalore

Name of the work : Improvements to cement Concrete Roads at Difence Colony in Bagalagunte in Ward No.14, BBMP, Bangalore.

Reference : EE/DD/WO/129/2017-18 Dated:18.12.2017

Sample ID : Cement Concrete

Size of cubes : 150mmx150mmx150mm

Cross Sectional Area : 22500 mm^2

Technical Reference : IS: 516-1959 (Reaffirmed 2008)

Grade of Concrete : M_{30}

Compressive Strength as on : 7th day

Sl.No.	Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	22.12.2017	29.12.2017	8.226	480.6	21.36
2	22.12.2017	29.12.2017	8.274	512.5	22.78
3	22.12.2017	29.12.2017	8.216	528.3	23.48

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 15 days from the date of testing.

For CIVIL QUALITY CONSULTANTS & ENGINEERS

Authorised Signatory

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರ
ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿಬಿಎಂಪಿ
ಬೆಂಗಳೂರು

CIVIL QUALITY CONSULTANTS & ENGINEERS

(Buildings Geo-Tech & Highway Materials Testing Laboratory)
An ISO 9001: 2008 Certified Company

JAS-ANZ
ISO 9001:2000 CERTIFIED

Job No.: CQCE/BBMP/SLE/W.No.14/2017-18 29.12.2017

TEST REPORT ON COMPRESSIVE STRENGTH OF CONCRETE CUBES

Client : **Executive Engineer,** Dasarahalli Division, BBMP, Bangalore.

Agency : **M/s. Shri Lakshmi Enterprises,** Bangalore

Name of the work : Improvements to cement Concrete Roads at Difence Colony in Bagalagunte in Ward No.14, BBMP, Bangalore.

Reference : EE/DD/WO/129/2017-18 Dated:18.12.2017

Sample ID : Cement Concrete

Size of cubes : 150mmx150mmx150mm

Cross Sectional Area : 22500 mm^2

Technical Reference : IS: 516-1959 (Reaffirmed 2008)

Grade of Concrete : M_{30}

Compressive Strength as on : 7th day

Sl.No.	Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	22.12.2017	29.12.2017	8.258	492.6	21.89
2	22.12.2017	29.12.2017	8.282	506.1	22.49
3	22.12.2017	29.12.2017	8.261	518.3	23.04

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 15 days from the date of testing.

For CIVIL QUALITY CONSULTANTS & ENGINEERS

Authorised Signatory

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ದಾಸರಹಳ್ಳಿ ವಲಯ-ಎಫ್‌ಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿಬಿಎಂಪಿ
ಬೆಂಗಳೂರು

CIVIL QUALITY CONSULTANTS & ENGINEERS

(Buildings Geo-Tech & Highway Materials Testing Laboratory)
An ISO 9001: 2008 Certified Company

JAS-ANZ
ISO 9001:2000 CERTIFIED

Job No.: CQCE/BBMP/SLE/W.No.14/2017-18 29.12.2017

TEST REPORT ON COMPRESSIVE STRENGTH OF CONCRETE CUBES

Client : **Executive Engineer,** Dasarahalli Division, BBMP, Bangalore.

Agency : **M/s. Shri Lakshmi Enterprises,** Bangalore

Name of the work : Improvements to cement Concrete Roads at Difence Colony in Bagalagunte in Ward No.14, BBMP, Bangalore.

Reference : EE/DD/WO/129/2017-18 Dated:18.12.2017

Sample ID : Cement Concrete

Size of cubes : 150mmx150mmx150mm

Cross Sectional Area : 22500 mm^2

Technical Reference : IS: 516-1959 (Reaffirmed 2008)

Grade of Concrete : M_{30}

Compressive Strength as on : 7th day

Sl.No.	Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	22.12.2017	29.12.2017	8.254	524.7	23.32
2	22.12.2017	29.12.2017	8.285	500.6	22.25
3	22.12.2017	29.12.2017	8.263	472.0	20.98

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 15 days from the date of testing.

For CIVIL QUALITY CONSULTANTS & ENGINEERS

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಕೆ.ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ ವಿಎಂಡಿ
ಬೆಂಗಳೂರು

Authorised Signatory

CIVIL QUALITY CONSULTANTS & ENGINEERS

(Buildings Geo-Tech & Highway Materials Testing Laboratory)
An ISO 9001: 2008 Certified Company

JAS-ANZ
ISO 9001:2000 CERTIFIED

Job No.: CQCE/BBMP/SLE/W.No.14/2017-18 29.12.2017

TEST REPORT ON COMPRESSIVE STRENGTH OF CONCRETE CUBES

Client : **Executive Engineer,** Dasarahalli Division, BBMP, Bangalore.

Agency : **M/s. Shri Lakshmi Enterprises,** Bangalore

Name of the work : Improvements to cement Concrete Roads at Difence Colony in Bagalagunte in Ward No.14, BBMP, Bangalore.

Reference : EE/DD/WO/129/2017-18 Dated:18.12.2017

Sample ID : Cement Concrete

Size of cubes : 150mmx150mmx150mm

Cross Sectional Area : 22500 mm^2

Technical Reference : IS: 516-1959 (Reaffirmed 2008)

Grade of Concrete : M_{30}

Compressive Strength as on : 7th day

Sl.No.	Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	22.12.2017	29.12.2017	8.362	527.8	23.46
2	22.12.2017	29.12.2017	8.339	516.2	22.94
3	22.12.2017	29.12.2017	8.347	500.3	22.24

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 15 days from the date of testing.

For CIVIL QUALITY CONSULTANTS & ENGINEERS

Authorised Signatory

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಡಿ.ದಾಸರಹಳ್ಳಿ ವಿಭಾಗ-ಎಫ್‌ಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿಬಿಎಂಪಿ
ಬೆಂಗಳೂರು